



# POLYGLASS Polywool Duct Wrap

**For Comfort and  
Energy Saving**

*Polywool Insulation for Air Handling*

## POLYWOOL DUCT WRAP

### **Acoustical Performance**

Tested Method ASTM C423. Type 'A' mounting.

Density kg/m <sup>3</sup>	Thickness (mm)	Centre Frequency (Hz)						
		125	250	500	1000	2000	4000	NRC
16	25	0.23	0.31	0.58	0.80	0.87	0.95	0.65
24	25	0.24	0.36	0.67	0.87	0.88	0.92	0.70
32	25	0.19	0.35	0.71	0.86	0.94	0.97	0.70
48	25	0.22	0.38	0.80	0.91	0.96	0.99	0.75
16	50	0.39	0.68	1.06	1.03	0.91	0.98	0.91
24	50	0.36	0.64	1.04	1.06	1.05	1.10	0.95
32	50	0.38	0.72	1.11	1.07	1.04	1.07	1.00

### **Range of Products Available (PLAIN / UNFACED)**

Density kg/m <sup>3</sup>	Thickness (mm)	Width (m)	Length (m)
16	25	1.2	20 / 30
16	50	1.2	15
24	25	1.2	24
24	50	1.2	12
32	25	1.2	20
32	50	1.2	10
48	25	1.2	15
48	50	1.2	7.5



## POLYWOOL SLAB

### **Range of Products Available (PLAIN / UNFACED)**

Density kg/m <sup>3</sup>	Thickness (mm)	Width (m)	Length (m)
32	(25/50)	1.2	2.3
48	(25/50)	1.2	2.3
64	(25/50)	1.2	2.3
80	(25/50)	1.2	2.3
96	(25/50)	1.2	2.3

\* 25mm @ 10 pcs/bale

\* 50mm @ 5 pcs/bale

